

Optical Properties of Metallic Systems

A Thesis presented for the degree of

Doctor of Philosophy

by

Martin Giles Blaber

B. Sc. Hons. (Nanotechnology): University of Technology, Sydney

Institute for Nanoscale Technology

Department of Physics and Advanced Materials

Faculty of Science

University of Technology, Sydney

March 2010

To my parents

Certificate of Originality

I certify that the work in this thesis has not previously been submitted for a degree nor has it been submitted as part of the requirements for a degree, except as fully acknowledged within the text.

I also certify that the thesis has been written by me. Any help that I received in my research work and the preparation of the thesis itself has been acknowledged. In addition, I certify that all information sources and literature used are indicated in this thesis.

A part of section 2.3 contains data submitted as part of the requirements of a previous degree, and is acknowledged in the text. The remainder of chapter 2 as well as chapters 3 and 4 are based on articles written by me under the guidance of my supervisors, with the notable exception of sections 3.1 and 3.2 which are based on an article largely prepared by Matthew Arnold, of which I am a co-author. Chapter 5 presents my understanding of the background theory used in later chapters. Where the derivation of a particular author has been followed closely it is noted in the text. Chapters 6 and 7 are also based on articles written by me under the guidance of my supervisors.



Martin Giles Blaber

Acknowledgements

Firstly, and foremost, I would like to thank my supervisors Prof. Mike Ford and Dr. Matthew Arnold. Their support over the last three years has been no less than amazing. A warm thanks to Prof. Mike Cortie, Director of the Institute for Nanoscale Technology (INT) at the University of Technology, Sydney (UTS), which supported me both financially, and by providing a lively and thought provoking place to work. INT also provided funding for all of the conferences I've attended.

I must thank Burak Cankurtaran and Rainer Hoft for teaching me much of what I know about density functional theory, and also Meredith Jordan for answering my silly questions and George Bacskey for allowing me to sit in on his quantum chemistry lectures at the University of Sydney.

Thanks to Andrew McDonagh, for providing a wealth of information regarding chemistry.

Past and present UTS grad students, Nadine Harris, Dakrong Pissuwan, Dylan Riessen, Vijay Bhatia, Tim Lucey and Supitcha Pew; thanks for putting up with me.

I would also like to thank Paul West, Vladimir Shalaev and Alex Kildishev from Purdue University, for showing me around their nanofabrication facility, and many usefull discussions on alternative materials for plasmonics. And also Kevin MacDonald from the University of Southampton for helpful suggestions regarding one of the manuscripts this work is based on.

Finally, Jonathan Edgar and Jana Krčmářová for enjoining me to maintain some semblance of sanity over the years, with many entertaining discussions, unlimited caffeine, and above all, friendship.

Computing Facilities were provided by the Australian Centre for Advanced Computing and Communication (ac3) in New South Wales and the National Computing Infrastructures (NCI) national facility at the Australian National University (ANU). This work was supported financially by the Australian Research Council (ARC), the Institute for Nanoscale Technology, the Department of Physics and Advanced Materials and the University of Technology, Sydney.

Contributing Publications

Publications that contributed to this work. (In order of publication)

- (P1) M G Blaber, N Harris, M J Ford, and M B Cortie, Proceedings of the IEEE: International Conference on Nanoscience and Nanotechnology, page 561 (2006).
“Optimisation of absorption efficiency for varying dielectric spherical nanoparticles”
- (P2) M G Blaber, M D Arnold, N Harris, M J Ford, and M B Cortie, Physica B **394**, 184 (2007).
“Plasmon absorption in nanospheres: A comparison of sodium, potassium, aluminium, silver and gold”
- (P3) M G Blaber, M D Arnold and M J Ford, Journal of Physical Chemistry C **113**, 3041 (2009).
“Search for the Ideal Plasmonics Nanoshell: The Effects of Surface Scattering and Alternatives to Gold and Silver”
- (P4) M G Blaber, M D Arnold and M J Ford, Journal of Physics: Condensed Matter, **21**, 144211 (2009).
“Optical properties of intermetallic compounds from first principles: a search for the ideal plasmonic material”
- (P5) M D Arnold and M G Blaber, Optics Express, **17**, 3835 (2009).
“Optical performance and metallic absorption in nanoplasmonic systems”
- (P6) M G Blaber, M D Arnold and M J Ford, Journal of Physics: Condensed Matter, **22**, 095501 (2010).
“Designing materials for plasmonic systems: the alkali-noble intermetallics”
- (P7) M G Blaber, M D Arnold and M J Ford, Journal of Physics: Condensed Matter, **22**, 143201 (2010).
“A review of the optical properties of alloys and intermetallics for plasmonics”

Non-Contributing Publications

Publications which do not feature in this work. (In order of publication)

- J A Edgar, H M Zareie, M G Blaber, A Dowd, M B Cortie, Proceedings of the IEEE: International Conference on Nanoscience and Nanotechnology, page 32 (2008).
“Synthesis of hollow gold nanoparticles and rings using silver templates”
- N Harris, M D Arnold, M G Blaber, M J Ford, Journal of Physical Chemistry C **113**, 2784 (2009).
“Plasmonic Resonances of Closely Coupled Gold Nanosphere Chains”
- M G Blaber, M J Ford and M B Cortie in “Gold: Science and Applications”, edited by C Corti and R Holliday, CRC Press (2010).
“Chapter 2: The Physics and Optical Properties of Gold”
- M D Arnold, M G Blaber, M J Ford, N Harris, Optics Express **18**, 7528 (2010).
“Universal scaling of local plasmons in chains of metal spheres”

Oral Presentations

(Most recent first)

- M. G. Blaber, M. D. Arnold, M. J. Ford
Designing Materials for Nanoplasmonics
SMONP 2009 (2009, Melbourne, Australia)
- M. G. Blaber, M. D. Arnold, M. J. Ford
Alkali-Noble intermetallics as replacements for gold and silver
PECS 8 (2009, Sydney, Australia)
- M. G. Blaber, M. D. Arnold, M. J. Ford
Can Metal Alloys Advance Plasmonics?
AIPC 2008 (2008, Adelaide, Australia)
- M. G. Blaber, M. D. Arnold, M. J. Ford
Low Loss Optical Alloys for Plasmonics
ICONN 2008 (2008, Melbourne, Australia)
- M. G. Blaber, M. D. Arnold, N. Harris, M. J. Ford, M. B. Cortie
From Absorption Efficiency to Superlensing: Potassium
AMN3 (2007, Wellington, New Zealand)

Poster Presentations

- M. G. Blaber, M. D. Arnold, M. J. Ford
The Optical Properties of Alkali Noble Group 3 Alloys
ICEM 2008 (2008, Sydney, Australia)
- M. G. Blaber, M. D. Arnold, M. J. Ford
The Optical Properties of Alkali Noble Group 3 Alloys
WATOC 2008 (2008, Sydney, Australia)
- M. G. Blaber, M. D. Arnold, M. J. Ford and M. B. Cortie
The Optical Properties of Gold Alloys
Molecular Modelling 2007 (2007, Melbourne, Australia)
- M. G. Blaber, M. J. Ford, M. B. Cortie
Plasmon absorption in a gold nanoparticle dimer
ETOPIM7 (2006, Sydney, Australia)

Contents

Certificate of Originality	ii
Acknowledgements	iii
Contributing Publications	iv
Non-Contributing Publications	v
Oral Presentations	vi
Poster Presentations	vii
Glossary of Acronyms	xv
Abstract	xvii
1 Introduction	1
2 Nanospheres and Nanoshells	3
2.1 Introduction	3
2.2 Theoretical Background	6
2.2.1 Spheres	6
2.2.2 Concentric Shells	7
2.2.3 Surface Scattering	8
2.3 Nanospheres	10
2.4 Nanoshells	11
2.4.1 Shells: Without Surface Scattering	12
2.4.2 Shells: With Surface Scattering	15
2.4.3 Nanoshells: Optimum Geometries	15
2.5 Conclusions	17
3 The Plasmonic Performance of Metals	19
3.1 Introduction	19
3.2 Geometry Specific Quality Factors	21
3.2.1 Nanoparticle Resonances	21
3.2.2 Plasmonic Superlens	23
3.2.3 Surface Plasmon Polaritons	24

3.3 Generic System Quality Factors 27

3.4 The Ideal Plasmonic Material 30

 3.4.1 Model Interband Transitions 31

3.5 Conclusions 37

3.6 References for Figure 3.9 39

4 Optical properties of metallic materials 40

4.1 Introduction 40

4.2 The Optical Properties of Alloys 43

 4.2.1 Noble Metal Alloys 43

 4.2.2 Transition Metal Alloys 45

 4.2.3 Summary of Alloys 45

4.3 Intermetallic Compounds 45

 4.3.1 Alkali Metal Binary Intermetallics 45

 4.3.2 Noble Metal Binary Intermetallics 46

 4.3.3 Group 13 Binary Intermetallics 48

 4.3.4 Other Binary Intermetallics 50

 4.3.5 Ternary Intermetallic Compounds 50

4.4 The Optical Properties of Silicides 52

4.5 High Pressure Materials 55

4.6 Liquid Metals and Glassy/Amorphous Materials 57

 4.6.1 Liquid Metals 58

 4.6.2 Amorphous/Glassy Alloys 59

4.7 Conclusions 61

5 Optical Response from First Principles 64

5.1 Introduction 64

5.2 The Dielectric Function 66

5.3 The Many Body Problem 71

5.4 Density Functional Theory 73

 5.4.1 Hohenberg-Kohn Theorems 74

 5.4.2 Kohn-Sham Formalism 76

 5.4.3 Exchange-Correlation Potentials 79

5.5 Numerical Considerations 80

 5.5.1 Pseudopotentials 80

 5.5.2 Basis Sets 85

5.5.3	Structural Optimisation	89
5.5.4	Phonons and Density Functional Perturbation Theory	90
5.6	A Comparison of Calculated Dielectric Functions	92
5.6.1	SIESTA	92
5.6.2	Spin-Orbit Coupling in Gold	93
5.6.3	Gold: Permittivity including local fields and electron-phonon scattering.	94
5.7	Concluding Remarks	95
6	Optical Alloys	96
6.1	Introduction	96
6.2	Method	97
6.3	Optical Properties of intermetallic compounds	99
6.3.1	Noble-Group 13 compounds	99
6.3.2	Alkali-Noble-group 13 compounds	101
6.3.3	Alkali-noble compounds	104
6.4	Conclusions	109
7	The Alkali-Noble Intermetallics	111
7.1	Introduction	111
7.2	Method	112
7.3	Results	116
7.3.1	The Performance of Local Surface Plasmon Modes	118
7.3.2	The Performance of Propagating Surface Plasmon Modes	121
7.4	Local Field Effects	123
7.5	Conclusions	123
8	Concluding Remarks and Future Work	125
8.1	Concluding Remarks	125
8.2	Future Work	126
8.2.1	CsCl Binary Intermetallics	126

List of Figures

2.1	The optimised absorption efficiency of free electron metal nanospheres.	12
2.2	Optimised absorption spectra for nanoshells.	13
2.3	Local surface plasmon quality factor calculated for various metals from experimental optical data.	13
2.4	Optimised absorption efficiency for nanoshells including surface scat- tering.	16
3.1	Operating point and loss in metals	20
3.2	Comparison of general metric for the resonance quality of a nanoshell with the retarded solution.	23
3.3	Comparison of general metric for the resonance quality of an ellipsoid with the retarded solution.	24
3.4	Comparison of metals using general metrics for the resolution of single and multi-layer superlenses.	25
3.5	Permittivity dependence of the resolution of multi-layer superlenses. .	25
3.6	Depiction of the geometry of commonly studied waveguiding structures.	26
3.7	Propagation constants for various SPP geometries.	27
3.8	Transverse field penetration into the dielectric as a function of prop- agation length.	28
3.9	Periodic table of the elements coloured by maximum local surface plasmon quality factor.	29
3.10	Surface plasmon quality data for alkali and noble metals.	31
3.11	Surface plasmon quality data for group 13 and some transition metals.	32
3.12	Permittivity of silver and gold	33
3.13	The effect of Band distribution on local surface plasmon quality factors	35
3.14	The effect of the number of electrons involved in interband transitions on local surface plasmon quality factors	36
3.15	The effect of the ratio of optical gap to plasma frequency on local surface plasmon quality factors.	37
3.16	The effect of the ratio of optical gap to plasma frequency on surface plasmon polariton quality factors.	38
4.1	Quality factors for iron silicides	54

4.2	Local surface plasmon quality factors for group 5 transition metal silicides.	55
4.3	Experimental imaginary permittivity of cobalt silicides in various stoichiometries.	56
4.4	The effect of pressure on the plasma frequency of metals.	57
4.5	Optical data for solid and liquid sodium	59
4.6	Optical data for solid and liquid aluminium	60
4.7	Optical data for solid and liquid gallium	61
4.8	Optical data for solid and liquid sodium	62
4.9	Optical data for some metallic glasses	63
5.1	Imaginary permittivity of gold using a local numerical orbit basis set: comparison with experiment.	93
5.2	Effect of spin orbit coupling on the band structure of gold.	94
5.3	Optical Response of gold.	95
6.1	Crystal Structure of Noble-Group 13, Alkali-Noble and Alkali-Noble-Group 13 compounds.	99
6.2	Interband transition spectra for various noble-group 13 compounds. Due to uniform broadening over the entire spectrum the transition probability at zero energy is positive.	100
6.3	Experimental imaginary permittivity of Li_2AgIn and Li_2CdIn	102
6.4	Interband transition spectra of all the A2 compounds. White bars indicate the position of the plasma frequency. The magnitude of ϵ'' has been truncated to 20 to aid visibility.	103
6.5	Interband transition spectra of all the Alkali-Noble ₂ compounds.	103
6.6	Comparison of the plasma frequency as calculated by the random phase approximation (RPA) and that calculated by the standard Drude free-electron gas formalism. N = noble, G = group 13.	104
6.7	Optical properties of (A) the alkali Ag and (B) the alkali Au compounds. Vertical lines represent the position of the plasma frequency for those compounds with $\omega_p < 6.0\text{eV}$	105
6.8	Imaginary permittivity in alkali-noble compounds with band edge to plasma frequency ratio better than gold.	106
6.9	Band diagram for alkali Ag compounds.	107
6.10	Band diagram for alkali Au compounds.	107
6.11	Transition diagram of KAg	108

7.1 The real part of the permittivity including the intraband contribution for the alkali-noble intermetallics including local field effects. 117

7.2 The interband contribution to the imaginary part of the permittivity for the alkali-noble intermetallics including local field effects. 118

7.3 The resonance quality of a localised surface plasmon as a function of the real permittivity from first principles. 119

7.4 Comparison of calculated local surface plasmon quality factors for the alkali-noble binary intermetallics with the most favourable experimental values for silver. 121

7.5 The resonance quality of a surface plasmon polariton as a function of the real permittivity from first principles. 122

7.6 Comparison of the effect of local fields on the maximum interband transition with the minimum interstitial electron density for the alkali noble intermetallics. 124

8.1 Plasma Frequency, ω_p , for non-noble-gas binary compounds in the CsCl structure. 127

8.2 Optical Gap, ω_g , for non-noble-gas binary compounds in the CsCl structure. Only compounds that are metallic, and have an optical gap above 1 eV are shown. 128

List of Tables

2.1	Optical data used for the addition of billiard scattering to the bulk experimental permittivity.	9
2.2	Shell geometries for optimised absorption efficiency with and without surface scattering	12
3.1	Optical Constants of some alkali, noble and group-13 metals, including the residual low frequency term caused by interband transitions .	33
3.2	Drude parameters for Ag, Au, Al, Na and K	38
3.3	References for the optical properties of the elements presented in Figure 3.9.	39
4.1	Optical constants of various transition metal silicides	53
6.1	Plasma frequency and secondary band edge of noble-group 13 compounds.	101
6.2	Band edges for selected metals and compounds.	105
6.3	Band edges for selected metals and compounds.	106
7.1	Calculated lattice constants of Alkali-Noble intermetallics.	115
7.2	Optical and Electronic data for the alkali noble intermetallics. Temperature dependent quantities are given at 300K.	116
7.3	Optical data for the alkali-noble intermetallics and gold.	120
7.4	The effect of the inclusion of local fields on the magnitude of the band edge in the alkali-noble intermetallics.	123

Glossary of Acronyms

AE	All-Electron
BE	Band Edge/Optical Gap
CG	Conjugate Gradients
DFPT	Density Functional Perturbation Theory
DFT	Density Functional Theory
DOS	Density Of States
DZP	Double- ζ plus Polarisation
EEL	Electron Energy Loss
EELS	Electron Energy Loss Spectroscopy
FP	Full Potential
GGA	Generalised Gradient Approximation
JC	Johnson and Christy
LAPW	Linearised, Augmented Plane Wave (method)
LCAO	Linear Combination of Atomic Orbitals
LDA	Local Density Approximation
LDOS	Local Density Of States
PBE	Perdew-Burke-Ernzerhof (GGA parameterisation)
PDOS	Projected Density Of States
P	Palik
PP	Pseudopotential
PW	Plane Wave
PW92	Perdew & Wang 1992 (LDA parameterisation)
SCF	Self-Consistent Field
SZP	Single- ζ plus Polarisation
TDCDFT	Time-Dependent Current Density Functional Theory
TDDFT	Time-Dependent Density Functional Theory
WF	Weaver and Frederikse

ϵ	Complex permittivity
ϵ'	Real part of the permittivity
ϵ''	Imaginary part of the permittivity
ϵ_{ib}	Interband contribution to the permittivity
ϵ_{∞}	Core polarizability, occasionally used to describe residual effects.
ϵ_i	Single particle eigenvalues
λ	Wavelength. Also, perturbation parameter
\mathbf{k}	Wave vector
ω	Angular Frequency (eV)
ω_g	Optical gap/band edge (eV)
ω_p	Bare or Drude plasma frequency (eV)
ω_s	Screened plasma frequency (eV)
$\omega_{\epsilon''_{max}}$	ω at which ϵ'' is greatest (refers to interband)
$\omega_{Q_{LSP}^{max}}$	ω at which Q_{LSP} is greatest
ψ	Single particle wavefunction
ϕ	Pseudo atomic orbital, or, generic basis function
ρ_{DC}	DC resistivity ($\mu\Omega\text{cm}$)
\mathbf{q}	Electron momentum. Also, phonon momentum
Q_{abs}	Absorption efficiency
Q_{ext}	Extinction efficiency
Q_{LSP}	Local Surface Plasmon quality
Q_{sca}	Scattering efficiency
Q_{SPP}	Surface Plasmon Polariton quality
σ	Optical conductivity
u	Pseudo-wavefunction
x	Size parameter ($2\pi r/\lambda$)

The continuous improvement of nanoscale fabrication techniques will ultimately result in a situation where the performance of plasmonic devices is not dependent on engineering defects, but rather on the fundamentally limiting behaviour of the underlying metals. This thesis addresses the following questions: Are silver and gold the best metals for plasmonics? What other materials are available? and finally; Can we design better plasmonic materials?

To answer these questions, classical electrodynamics calculations are performed using tabulated dielectric functions from the literature. Starting from a comparison of nanoshells made of various free electron metals, it is shown that the low plasma frequency metals sodium and potassium perform well. However, these metals are not suitable for many common uses of nanoshells. As such, the material choice is extended to all non f -group metals in the periodic table and a variety of additional geometries are studied, including nanorods, superlenses and a number of guiding structures. It is shown that gold, silver, the alkali metals and aluminium outperform all other metals, each over a range of frequencies and permittivities. None of the reviewed elements performs better than silver and gold.

As none of the elements seem to offer any advantage over silver or gold, the search is extended to alternative materials with tabulated dielectric functions. A review of the plasmonic properties of these materials is presented, including alloys, intermetallic compounds, high pressure materials as well as silicides, metallic glasses, and liquid metals. It is discovered that liquid sodium outperforms its solid elemental counterpart. Additionally, several materials with simple crystal structures seem to perform well, but none to the extent of silver or gold.

The number of compounds for which tabulated optical constants are available is severely limited. In order to evaluate the performance of a large number of materials, first principles quantum mechanical calculations must be performed. It is shown that the plasmonic performance can be approximately gleaned from the relationship between the optical gap and the plasma frequency. However, in order to compare the calculated optical response of materials with experimental data for the elements, the Drude phenomenological scattering rate must be known. Here, for the first time, calculations of the real and imaginary components of the dielectric function including the electron-phonon scattering rate are performed in order to gauge the plasmonic performance of materials with no tabulated optical data.

A list of publications associated with this work is presented on page iv.